

CSS V-Wrap™ HMPCA

Precured Carbon Fiber Anchor



DESCRIPTION

CSS V-Wrap HMPCA is a high-strength, high-modulus, non-corrosive precured carbon anchor designed to be partially field laminated with CSS V-Wrap 770 epoxy to create a carbon fiber reinforced polymer (CFRP) composite anchor for enhanced detailing of CSS V-Wrap fabrics. The portion of the anchor intended to be embedded into the substrate is factory saturated and precured.

MATERIAL PROPERTIES

Dry Fiber Properties	
Tensile Strength	670,000 psi (4,600 MPa)
Tensile Modulus	37 x 10 ⁶ psi (260,000 MPa)
Elongation at Break	1.65%

Cured Composite Properties ^{1, 2}	
Property	Design Value
Tensile Strength	128,000 psi (880 MPa)
Tensile Modulus	14,200 ksi (98 GPa)
Elongation at Break	0.9%

1. When laminated with CSS V-Wrap 770 saturant resin and post cured for 48 hours at 140°F.

2. In primary fiber direction.

PERFORMANCE FEATURES

- Manufactured using ICC-approved raw materials
- High tensile modulus and strength
- Lightweight
- Noncorrosive
- Flexible
- Various finish options

APPLICATIONS

The CSS V-Wrap HMPCA carbon fiber anchor is combined with CSS V-Wrap epoxies and can be used as a standalone reinforcement or to improve end details and anchorage of various CSS V-Wrap designs.

- Load increases
- Seismic strengthening
- Repair of structural elements
- Change in structural system
- Design or construction defects

PACKAGING

Custom anchor lengths and diameters; available in diameters ranging from 0.375" to 1.5" (9 mm to 37 mm) in 1/8" increments.

Design

The CSS V-Wrap HMPCA carbon fiber anchors shall be designed to meet specific design criteria. The criteria for each project is dictated by the Engineer of Record and any relevant building codes and/or guidelines. Contact Structural Technologies at (410) 859-6502 for engineering support with anchor design.

Surface Preparation

Surfaces to receive CSS V-Wrap HMPCA must be clean and sound. They must be dry and free of frost. All dust, laitance, grease, curing compounds, waxes, deteriorated materials and other bond-inhibiting materials must be removed from the surface prior to application. Existing uneven surfaces must be filled with appropriate epoxy putty or repair mortar. Use abrasive blasting, pressure washing, shotblasting, grinding or other approved mechanical means to achieve an open-pore texture with a concrete surface profile of not less than CSP-3 (ICRI). In certain applications and at the engineer's discretion, the bond between the substrate and the fabric may be determined to be non-critical (such as in column confinement applications). The adhesive bond strength of the concrete may be verified after surface preparation by random pull-off testing (ASTM C1583) at the discretion of the engineer. Minimum tensile strength of 200 psi must be achieved for concrete.

Drilled Hole Preparation

Drill holes to specified diameter, depth and angle according to approved drawings using a rotary hammer drill, a carbide-tipped drill bit conforming to ANSI B212.15-1994, router bits, and a Simpson Strong-Tie® ETB brush. Drilled hole diameter shall be anchor diameter plus 1/8" (3.18 mm). Round the top edge of the drilled hole using router bits to specified radius. Using clean, compressed air, blow out any remaining debris for four seconds, then clean with the appropriate sized Simpson Strong-Tie ETB brush for a minimum of four cycles, and again blowing out any remaining debris for another four seconds with compressed air.

Application

Manually saturate the loose fiber portion of the anchor and ensure full fiber saturation is achieved. Install the anchor in accordance with the approved project drawings and specifications. Refer to the CSS V-Wrap 770 Epoxy Saturant Technical Data Sheet for all information on the approved epoxy.

CAUTION

Protective Measures: The use of safety glasses and chemical-resistant gloves is recommended. Use appropriate clothing to minimize skin contact. The use of a NIOSH-approved respirator is required to protect respiratory tract when ventilation is not adequate to limit exposure below the permissible exposure limit (PEL). Refer to Safety Data Sheets (SDS) available at strongtie.com/sds for detailed information.

FIRST AID

Skin: Wash fibers off skin with water and soap. If fibers are embedded in the skin, remove with tweezers. Discard clothing that may contain embedded fibers. Seek medical advice if exposure results in adverse effects.

Eyes: Immediately flush with a continuous water stream for at least 20 minutes. Washing immediately after exposure is expected to be effective in preventing damage to the eyes. Seek medical advice.

Inhalation: If there is inhalation exposure to the fibers of this product, remove source of exposure and move affected person to fresh air. If affected person is not breathing, give artificial respiration. If there is breathing difficulty, give oxygen. Seek medical advice for any respiratory problems.

Ingestion: Ingestion is not a likely form of exposure to this product. If ingestion does occur, DO NOT INDUCE VOMITING. Administer nothing by mouth if affected person is unconscious. Seek medical advice.

CLEANUP

ENVIRONMENTAL PRECAUTIONS

Spill/Release and Cleanup Procedures: In case of spill, collect (e.g., sweep up, vacuum) spilled material and either reuse or dispose of properly. Chopped or milled carbon fibers may be slippery if spilled, posing an accident risk. Wear personal protective equipment as described in the MSDS during cleanup activities.

LIMITED WARRANTY

This product is covered by the Simpson Strong-Tie RPS Product One-Year Limited Warranty, which is available at strongtie.com/limited-warranties or by calling Simpson Strong-Tie at (800) 999-5099.

IMPORTANT INFORMATION

It is the responsibility of each purchaser and user of each Product to determine the suitability of the Product for its intended use. Prior to using any Product, consult a qualified design professional for advice regarding the suitability and use of the Product, including whether the capacity of any structural building element may be impacted by a repair. As jobsite conditions vary greatly, a small-scale test patch is required to verify product suitability prior to full-scale application. The installer must read, understand, and follow all written instructions and warnings contained on the product label(s), Product Data Sheet(s), Safety Data Sheet(s), and the strongtie.com website prior to use. For industrial use only by qualified applicators. KEEP OUT OF REACH OF CHILDREN!

 **WARNING!** Cancer and reproductive harm — www.P65Warnings.ca.gov.